

Membrane Element

SWC6 MAX

Performance:

	Low Pressure:	High Flow:
Permeate Flow:	6,600 gpd (25 m ³ /d)	13,200 gpd (50 m ³ /d)
Salt Rejection:	99.6% (99.4 % min)	99.8% (99.7% min)
Boron Rejection (Typical) [†] :	83.0%	91.0%
Applied Pressure:	600 psi (4.1 MPa)	800 psi (5.4 MPa)

Type

Configuration:	Spiral Wound
Membrane Polymer:	Composite Polyamide
Membrane Active Area:	440 ft ² (40.8m ²)

Application Data*


Maximum Applied Pressure:	1200 psig (8.27 MPa)
Maximum Chlorine Concentration:	< 0.1 PPM
Maximum Operating Temperature:	113 °F (45 °C)
pH Range, Continuous (Cleaning):	2-11 (1-13)*
Maximum Feedwater Turbidity:	1.0 NTU
Maximum Feedwater SDI (15 mins):	5.0
Maximum Feed Flow:	75 GPM (17.0 m ³ /h)
Minimum Ratio of Concentrate to Permeate Flow for any Element:	5:1
Maximum Pressure Drop for Each Element:	10 psi

* The limitations shown here are for general use. For specific projects, operating at more conservative values may ensure the best performance and longest life of the membrane. See Hydranautics Technical Bulletins for more detail on operation limits, cleaning pH, and cleaning temperatures.

Test Conditions

The stated performance is initial (data taken after 30 minutes of operation), based on the following low pressure conditions:

32,000 ppm NaCl
 600 psi (4.1 Mpa) Applied Pressure
 77 °F (25 °C) Operating Temperature
 10% Permeate Recovery
 6.5 - 7.0 pH Range



A, inches (mm)	B, inches (mm)	C, inches (mm)	Weight, lbs. (kg)
40.0 (1016)	7.89 (200)	1.125 (28.6)	36 (16.4)

Notice: Permeate flow for individual elements may vary +25% or -15%. Membrane active area may vary +/-4%. All membrane elements are supplied with a brine seal, interconnector, and o-rings. Elements are enclosed in a sealed polyethylene bag containing less than 1.0% sodium meta-bisulfite solution, and then packaged in a cardboard box.

[†]When tested at standard test conditions with 5.0 ppm Boron in feed solution.

Hydranautics believes the information and data contained herein to be accurate and useful. The information and data are offered in good faith, but without guarantee, as conditions and methods of use of our products are beyond our control. Hydranautics assumes no liability for results obtained or damages incurred through the application of the presented information and data. It is the user's responsibility to determine the appropriateness of Hydranautics' products for the user's specific end uses. 11/01/11